




(10) Correspondence to the free electron model



(11) Electron band




(12) 2-Dimensional Square Lattice



(12) 2-Dimensional Square Lattice

$$E = \alpha + 2\beta \cos k_x a + 2\beta \cos k_y a$$




Bandwidth: 8β

(In general, bandwidth is $2z\beta$, where z is the coordination number (the number of the nearby sites.))




(12) 2-Dimensional Square Lattice

$$E = \alpha + 2\beta \cos k_x a + 2\beta \cos k_y a$$



(12) 2-Dimensional Square Lattice

Copper oxide high-temperature superconductor




$\text{La}_2\text{Cu}^{2+}\text{O}_4 \rightarrow \text{Cu} : d^9 \rightarrow d_{x^2-y^2}$ band has one electron (Half-filled)

(13) Tight-bonding method for more than two atoms in a cell

LCAO-MO $\phi = \sum_i c_i \chi_i$

For 2 atoms, $i=1, 2$



Bloch function is made from χ_i for the whole crystal.

$$\chi_i \rightarrow \sum_n e^{inka} \chi_i(n)$$

Crystal orbital is constructed instead of molecular orbital as,

$$\phi = \sum_i \sum_n c_i e^{inka} \chi_i(n)$$

Calculate $E = \frac{\int \phi^* H \phi d\tau}{\int \phi^* \phi d\tau}$ from this, and similarly to the usual Mo theory,

$\frac{\partial E}{\partial c_i} = 0$ leads to simultaneous equations of c_i , and the secular equation is

$$\begin{vmatrix} \alpha_{11}(k) - E & \beta_{12}(k) & \dots \\ \beta_{21}(k) & \alpha_{22}(k) - E & \dots \\ \vdots & \vdots & \ddots \end{vmatrix} = 0$$

Since χ_i is Bloch function, the matrix elements, α and β are functions of k :

$$\alpha_{ii}(k) = \int (\sum_m e^{-imka} \chi_i^*(m)) H (\sum_n e^{inka} \chi_i(n)) d\tau$$

$$= \alpha_i + \sum_n \beta_{ii}(n) e^{inka} \quad \beta_{ii}(n) = \int \chi_i^*(0) H \chi_i(n) d\tau$$


$$\beta_{ij}(k) = \int (\sum_m e^{-imka} \chi_i^*(m)) H (\sum_n e^{inka} \chi_j(n)) d\tau$$

$= \sum_n \beta_{ij}(n) e^{inka}$ When interaction β exists in the r direction, add a term βe^{ikr} .

$$\beta_{ij}(n) = \int \chi_i^*(0) H \chi_j(n) d\tau$$

(14) Energy band of one-dimensional alternating chain

β is alternately β_1 and β_2 .
 \rightarrow Two atoms 1 and 2 in a cell.



For simplicity, put $\langle \chi_1 | H | \chi_1 \rangle = \langle \chi_2 | H | \chi_2 \rangle = \alpha = 0$.

$$\langle \chi_1 | H | \chi_2 \rangle = \langle \chi_2 | H | \chi_1 \rangle^* = \beta_2 e^{-ika} + \beta_1 e^{ika}$$

β_2 in the $-a$ direction from 1


β_1 in the a direction from 1

Secular equation is,

$$\begin{vmatrix} -E & \beta_2 e^{-ika} + \beta_1 e^{ika} \\ \beta_2 e^{ika} + \beta_1 e^{-ika} & -E \end{vmatrix} = 0$$

The solution is depicted in the right:

$$1 + \cos 2x = 2 \cos^2 x$$



Excise 1D alternate chain

$$\begin{vmatrix} -E & \beta_2 e^{-ika} + \beta_1 e^{ika} \\ \beta_2 e^{ika} + \beta_1 e^{-ika} & -E \end{vmatrix} = 0$$

- 1) Solve the above secular equation, and obtain the following energy band:

$$E = \pm \sqrt{\beta_1^2 + \beta_2^2 + 2\beta_1\beta_2 \cos 2ka}$$

- 2) Obtain total bandwidth, W , and energy gap, E_g


$$W = 2|\beta_1 + \beta_2|$$

$$E_g = 2|\beta_1 - \beta_2|$$

- 3) Put $\beta_1 = \beta_2$, and resume the 1D uniform chain



$$E = \pm \sqrt{\beta^2 + \beta^2 + 2\beta^2 \cos 2ka} = \pm \beta \sqrt{2(1 + \cos 2ka)} = 2\beta \cos ka$$

This is the same as $E = \alpha + 2\beta \cos ka$ and $\alpha = 0$.




Different β for single and double bonds


$$\beta_1 \neq \beta_2$$




Reduced zone



Extended zone




Peierls Insulator: Long periodicity generates a new energy gap and makes the system insulating.




Metal



$$\beta_1 \neq \beta_2$$



Insulator



Energy band for a system with many atomic orbitals

LCAO-MO from all atomic orbitals in a cell
(N , each atom may have more than one.)

$$\phi = \sum_i c_i \chi_i$$

Make the Bloch function of each χ



$\chi_i \rightarrow \sum_n e^{inka} \chi_i(n)$ leading to an

$N \times N$ secular equation




$$\begin{vmatrix} \alpha_{11}(k) - E & \beta_{12}(k) & \dots \\ \beta_{21}(k) & \alpha_{22}(k) - E & \dots \\ \vdots & \vdots & \ddots \end{vmatrix} = 0$$

Since each element is a function of k ,
this secular equation is solved at each k , to give
 N energy levels.


These energy levels for different k are connected
to afford continuous energy bands (right).





Ge atom



Energy band of Ge



Forgetting k



Energy gap (Band gap)
C 5.47 eV
Si 1.12 eV
Ge 0.66 eV


Semiconductor

Energy band of Ge

Energy bands of solids


Conduction band

Valence band




A unit of 1D energy band is $-\pi/a < k < \pi/a$

➡ 2D, 3D




Solid-state physics defines the k -space from e^{ika} : reciprocal lattice points at $2\pi/a$.
Crystallography defines the k -space from $e^{2\pi ika}$: reciprocal lattice points at $1/a$.


How to make the Brillouin zone.



How to make the Brillouin zone.




How to make the Brillouin zone for an oblique lattice.



Brillouin zone and the Bravais lattices


Reciprocal of centered is centered



Brillouin zone and the Bravais lattices

Reciprocal of face centered is body centered


Reciprocal of body centered is face centered



Brillouin zone and the Bravais lattices


体心立方格子
bcc
body centered
cubic

面心立方格子
fcc
face centered
cubic



Fermi surface of metals

(1) Alkali metals Li, Na, K




Fermi surface \Leftrightarrow trajectory of $k_F \Leftrightarrow$ Surface at $E=E_F=\text{const.}$

Assuming free electron

$$E = \frac{\hbar^2}{2m} (k_x^2 + k_y^2 + k_z^2) = \text{const.}$$

leads to a sphere in the k -space.



Fermi surface of alkali metals is not deviated from the perfect sphere by 1%.




Energy interval in the k -space is $\Delta k = \frac{2\pi}{Na}$

Volume of the Fermi sphere is half of the volume of the 1st Brillouin zone.


Fermi surface of metals

(1) Divalent metals Mg, Al


Volume of the Fermi sphere is the same as the volume of the 1st Brillouin zone.



第1ゾーン






第2ゾーン




第3ゾーン

Fermi surface of metals



(2) Divalent and trivalent Mg, Al



第1ゾーン



第2ゾーン




第3ゾーン

Fermi surface of metals

(3) Transition metals

3d band is narrower than the 4s band.

Approximately $s^1 d^{n-1}$





W: highest melting point (3380°C)
← strong bonds


Fermi surface of metals

(4) Cu, Ag, Au

$s^1 d^{10} \rightarrow$ close to alkali metals





Nearly a sphere but
Partly connected.



1D metal

$$E = \frac{\hbar^2 k_x^2}{2m} = \text{const.} \quad \text{leads to } k_x = k_F = \text{const.}$$


(No momentum for other k_y and k_z directions.
= cannot move.)



The Fermi surface consists of a pair of planes.


Examples of 1D metals

(1) 1D Platinum Complex KCP
 $\text{K}_2[\text{Pt}(\text{CN})_4]\text{Br}_{0.40}\text{xH}_2\text{O}$





Pt surrounded by CN
Metal 1D Chain

Metal at room temp.
Insulator at low temp.





Examples of 1D metals

(2) NbSe_3





(3) Polyacetylene



Examples of 1D metals


(4) Organic Charge-Transfer Complex (TTF)(TCNQ)




Current flow

Examples of 2D metals

$$E = \frac{\hbar^2}{2m} (k_x^2 + k_y^2) = \text{const.} \quad \text{leads to } k_x^2 + k_y^2 = k_F^2 = \text{const.} \rightarrow \text{circle}$$





Cylindrical Fermi surface



Examples
Graphite
Organic superconductors


Organics: energy levels → energy bands

A single molecule of TMTSF




Energy levels

A crystal of (TMTSF)₂PF₆




Energy bands



Consider only
HOMO (for donors) or
LUMO (for acceptors)

Energy band of organic conductors consists of only HOMOs.

Fermi surface of the first organic superconductor



β (meV)	HOMO
a1	200
a2	230
b	35
p1	20
p2	7

Direction	Interaction
1→1	±b
2→2	±b
1→2	a/2
	-a/2
	a/2 - b
	-a/2 + b
	p1
	p2

$$\beta_{11} = \beta_{22} = \beta_b e^{ikb} + \beta_b e^{-ikb} = 2\beta_b \cos(kb)$$

$$\beta_{12} = \beta_{21}^* = \beta_{a1} e^{ika/2} + \beta_{a2} e^{-ika/2} + \beta_{p1} e^{ika/2 - kb} + \beta_{p2} e^{-ika/2 + kb}$$


Put these in $\begin{vmatrix} \beta_{11} - E & \beta_{12} \\ \beta_{21} & \beta_{22} - E \end{vmatrix} = 0$ and solve to give:

(TMTSF)₂PF₆

$$E(k) = 2\beta_b \cos(kb) \pm \sqrt{\Delta}$$


$$\Delta = [(\beta_{a1} + \beta_{a2}) \cos(\frac{ka}{2}) + (\beta_{p1} + \beta_{p2}) \cos(\frac{ka}{2} - kb)]^2 + [(\beta_{a1} - \beta_{a2}) \sin(\frac{ka}{2}) + (\beta_{p1} - \beta_{p2}) \sin(\frac{ka}{2} - kb)]^2$$

β (meV)	HOMO
a1	200
a2	230
b	35
p1	20
p2	7
Calculated from MO	




A pair of waving planes → Quasi-1D conductor
Considerable waving reflects the 2D character.

Fermi surface of organic superconductor



$$\beta_{11} = \beta_{22} = \beta_c e^{ikc} + \beta_c e^{-ikc} = 2\beta_c \cos(kc)$$

$$\beta_{12} = \beta_{21}^* = \beta_{p1} + \beta_{p2} e^{i(kb+kc)} + \beta_{q2} e^{ikc} + \beta_{q1} e^{ikb}$$




Cylindrical Fermi surface indicated 2D.


Program available from <http://www.op.titech.ac.jp/lab/mori/lib/program.html>

Excise Band structure of the θ -phase

This generally found structure is called herringbone structure in organic crystals or alternatively θ -phase in organic conductors. Calculate the energy bands of this structure.



A unit cell contains two molecules, numbered 1 and 2. Transfer t_a , running along a, is between two Molecule 1. Transfer t_p , running diagonal ($a/2$, $b/2$) etc, is between Molecule 1 and 2.



- (1) How many Molecule 1 exist near Molecule 1?
From this, obtain the diagonal element F_{11} .
- (1) How many Molecule 2 exist near Molecule 1?
From this, obtain the nondiagonal element F_{12} .
- (3) Solve the secular equation, and obtain an equation of $E(k_a, k_b)$ representing the energy band.

$$\cos x + \cos y = 2 \cos \frac{x+y}{2} \cos \frac{x-y}{2}$$